

# Technical Data Sheet

## Ice9™ Flex

Thermally conductive, electrically non-insulating plastic  
Product code: TC-TPE1-145-000

Product type: filament or pellets  
Properties based on 3D printed samples



GENERAL PROPERTIES	VALUE
Base Material	Thermoplastic elastomer (TPE)
Color	Dark gray
Density	1550 kg/m <sup>3</sup>

THERMAL PROPERTIES	METRIC	ENGLISH	ASTM
Thermal conductivity, in-plane	8 W/m-K	54 BTU·in/hr·ft <sup>2</sup> ·°F	E1461
Thermal conductivity, through-plane	2.5 W/m-K	17 BTU·in/hr·ft <sup>2</sup> ·°F	E1461
Specific heat	1300 J/kg-K	0.31 BTU/lb·°F	E1269
Coefficient of thermal expansion	80 ppm/°C	44 ppm/°F	E831
Heat deflection temperature, 0.45 MPa	65 °C	149 °F	D648
Max. continuous temperature	110 °C	230 °F	*

MECHANICAL PROPERTIES	METRIC	ENGLISH	ASTM
Shore Hardness	88 A		D2240
Flexural modulus	95 MPa	15 ksi	D638
Tensile strength, Break	15 MPa	8 ksi	D638
Elongation at break	15 %	15 %	D638
Impact strength, Izod notched	No break	No break	D256

ELECTRICAL PROPERTIES	METRIC	ASTM
Volume resistivity	10 <sup>3</sup> Ω-cm	D257

\* Highest temperature recommended for operation of more than 1 hour and is based internal testing and not any recognized standard.

DISCLAIMER: This material is a proprietary composition of TCPoly, Inc. U.S. and international patents pending. The testing and product data provided in this data sheet are preliminary in nature accurate. The data contained herein are provided for preliminary informational purposes only and for initial evaluation of the product. As a result, they are not appropriate for the purpose of developing a final specification and should not be relied on for such specification purposes. TCPoly extends no warranties, makes no representations and assumes no responsibility as to the accuracy or suitability of this information or this product for any purchaser's or user's use or for any consequence of its use. TCPoly disclaims any warranty of merchantability or warranty of fitness for any particular use. All statements, technical information and recommendations contained herein are based on seller's or manufacturer's tests and the tests of others. Judgment as to the suitability of information herein for the user's purposes are necessarily the user's responsibility. Users shall determine the suitability of the products for the intended application.

# Recommended FDM Print Settings

## Ice9™ Flex

Thermally conductive, electrically non-insulating plastic  
Product code: TCP 01-1140-2210

Product type: FDM filament



### GENERAL PROPERTIES

---

Base material	Thermoplastic elastomer (TPE)
Color	Dark gray
Filament diameter	1.75 or 2.85 +/- 0.05 mm

### TEMPERATURE SETTINGS

---

	VALUE	UNITS
Extruder temperature	225-250	°C
Bed temperature	40-90	°C
Cooling fan	60%, Bridging Only	

### SLICING SETTINGS

---

	VALUE	UNITS
Print speed	20-40	mm/s
Layer	0.2-0.8	mm
Retraction distance	4-8	mm
Retraction Speed	30-50	mm/s
Coasting distance	0.2-0.5	mm
Infill for best thermal performance	95-100	%

### ADDITIONAL GUIDELINES

---

Nozzle diameter	0.4-1.0 mm
Extruder type (1.75 mm)	Direct only
Extruder type (2.85 mm)	Direct or Bowden
Print bed preparation	Painter's tape
Drying instructions	2 hr @ 70°C
Storage instructions	Sealed bag
Part removal from bed	Heat bed to 100°C then gently remove with spatula